

# **Chocolate Molds Silicone**

#### **Product Description:**


Chocolate Molds Silicone is great to make chocolate molds either with simple or intricate patterns. It have FDA Certificate and excellent for high-detail chocolate molds and design. Also it very suitable for making ice trays molds, baking molds, casting butter and other application you can image to produce foods.



## Appearance:

Part A: an non-toxic and odorless liquid in translucent color with platinum inside Part B: an non-toxic and odorless liquid in translucent color.

ATT: We do any curing time as you requirements



Web:www.ottsilicone.comPage 1Email:sz@ottsilicone.comTel:+86-020-86819712Email:gz@ottsilicone.com



#### Features:

- ♦ Amazing fluidity and easy to operate
- ♦ Platinum-based, food-grade silicone (environmental,odorless and nontoxic)
- ♦ Delicate design available
- ♦ Mixing ration: 1:1 for easy mixing ration
- ♦ Easy de-molding
- ♦ Excellent tension and tear strength
- ♦ High performance in duplication
- ♦ Excellent resistance to weather, temperature, aging, acid & aging-Proofing.
- ♦ High resistance to high temperature and aging(resist -60 to 250°C)

**Model Code:** J820#, J825#, J840#

#### Technical Data:

**Notes:** The data are based on the operation under room temperature of 25  $^{\circ}$ C.

Typical general characteristics	Inspection Method	Value		
Product data (Catalyzed A+B)		J820	J825	J840
Hardness	Shore A	20±2	25±2	40±2
Mix Ratio	A:B	1:1	1:1	1:1
Color	1	Translucent	Translucent	Translucent
Pot life	25 °C (77F)	20-40mins	20-40mins	20-40mins
Curing time	25 °C (77F)	3- 5hrs	3- 5hrs	3- 5hrs
Viscosity	mPa.s	6000±2000	7000±2000	15000±2000
Tear-Strength	kg/cm	≥26	≥24	≥22
Tensile -Strength	M.pa	≥6.0	≥6.3	≥6.8
Elongation	%	≥500	≥500	≥450
Shrinkage	%	≤0.1	≤0.1	≤0.1

Web:www.ottsilicone.comPage 2Email:sz@ottsilicone.comTel:+86-020-86819712Email:gz@ottsilicone.com



**Guangzhou OTT New Materials Co., Ltd.** 

#### Packing:

**Part A:** 1kg, 5kg, 10kg, 20kg, 25kg, 200kg, Vacuumed Packing in white color **Part B:** 1kg, 5kg, 10kg, 20kg, 25kg, 200kg, Vacuumed Packing in sky blue color



### Storage & Shelf Life:

1Year at least, stored in a cool and dry place under room temperature 25°C

#### **Operation Method:**

Both Pouring or brushing operation methods for our Chocolate Molds Silicone are available. You can chose the best one as your preference, we can provide thixotropic agent for Brushable.



#### Caution - Safety First !!!

- 1. Read the material safety data sheet(MSDS) before use.
- 2. Keep Out Of Reach Of Children.
- 3. Be careful. Use only with adequate ventilation. Contact with skin and eyes may cause irritation. Flush eyes with water for 15mins and seek immediate medical attention. Remove from skin with water-less hand cleaner followed by soap & water.



Web:www.ottsilicone.comPage 3Email:sz@ottsilicone.comTel:+86-020-86819712Email:gz@ottsilicone.com